



KapusKasing Operations

Book Paper Grades

Regular and 65 Brite

BWT - lbs 25x38x500	Grade #	BWT - g/m2	ISO Brightness	Average Caliper (microns)	Average Caliper (x0.0001in)	PPI
30	36/36B	45	56/65	76	3.3	600
30	55/55B	45	56/65	102	4.0	500
33	59/59B	48.8	56/65	114	4.5	450
33	56/56B	48.8	56/65	102	4.0	500
33	77/77B	48.8	56/65	127	5.0	400
35	78/78B	51.4	56/65	127	5.0	400

Notes:

- All values presented above (except caliper) are targets.
- Forest Stewardship Council® (FSC®) certified (FSC-C167905)